

## **Decofond Ready mix mortar for fine lime finishes**

### **St Astier Natural Hydraulic Limes (NHL)**

Backgrounds: most types, including plasterboard and painted surfaces and surfaces of different materials.

Natural colour: light grey.

Consumption: 1.8 kg x m<sup>2</sup> x mm of thickness

Packing: 15 kg tubs or 30 kg. bags

Shelf life: 6 months in sealed original bag, stored in dry conditions.

### **Application recommendations.**

Water addition:

3 to 3.5 litres per tub of 15 kg

6 to 7 litres per bag of 30 kg

Mix with a mortar whisk for maximum 5 minutes.

On a clean, straight surface, apply a coat of max. 5 mm. When different background materials meet, apply a mesh\* over the joint extending 150mm each side.

\* Mesh size : 10 x 10 mm.

### **Coloured fine finishes:**

Lime washes: apply when sufficiently dry.

Fresco finishes: apply when still fresh.

Fine finishes: All fine lime mortars finishes are acceptable. Color Chausable EF for steel float or sponge finishes is also acceptable.

Stucco/marmorino type finishes: when dry, use Decoliss (0-0.04mm stucco type St. Astier mortar, see relevant data sheet). This can be finished to a polish by qualified craftsmen.

### **See Also:**

[Interior Finishes](#) & [Health and Safety Information](#)

**The above details are given for general information purposes and do not constitute a specification.**

**For further Guidance, contact your St Astier Distributor.**

Copyright © Setra Marketing Ltd. 2006

