

POSE BRIQUES MORTAR - formulated for Masonry Clay Block Construction

Ready mixed mortar for thin joint construction with Bouyer Leroux clay blocks.

This is a proprietary mortar for the Bouyer Leroux BioBric and BGV ranges.

Composition: hydraulic binders, silica sands, water retainer, resin and setting control agent.

Packing: 25kg bags

Storage: keep dry

Shelf life: 8-12 months if properly stored.

Bulk density: 1350g per litre

Granulometry: <1mm

pH: 12.5

Water retention: 93%

Bonding strength: 0.5MPa

Compressive strength (28 days): M 10 (EN/BS 998.1)

Mixing: In adequate container with already some water in it, add the mortar and whisk (slowly to start with). Keep adding water and whisking until a paste consistency is achieved. Total water addition about 40% (10 litres per 25 kg. bag).

Consumption per 25kg bag	Biobric 37.5	8.6m ²
	Biobric 30	11m ²
	B G V	16.6m ²

Application: use specially designed mortar rollers

NOTE: once mixed, use within 15 minutes.

For further Guidance, contact your St Astier Distributor.

Copyright © Setra Marketing Ltd. 2006

